


Technical data

LINITHERM PAL

Universal insulation boards



Property	Formula symbol	Unit	Parameter and measured value	Standard
Material	-	-	Polyurethane rigid foam, coated with aluminium film on both sides, low-glare on one side	EN 13165
Application type	-	-	DAA dh bzw. DEO dh	DIN 4108-10
Gross density	ρ	kg/m ³	≥ approx. 33	-
Fire behaviour	-	-	Class E or normally inflammable	EN 13501-1
Thermal conductivity (D)	λ_B	W/(mK)	0.023	DIN 4108-4
Thermal conductivity (EU)	λ_D	W/(mK)	0.022	EN 13165
Temperature resistance	-	°C	-30 to +90	-
Compressive stress	σ_{D10}	N/mm ² kPa	≥ 0.12 (at 10 % compression) ≥ 120	EN 826
Max. permitted permanent compressive stress	σ_{D2}	N/mm ² kPa	≥ 0.02 (at 2 % compression) ≥ 20	-
Tensile strength perpendicular to the panel surface	σ_{mt}	N/mm ² kPa	≥ 0.05 ≥ 50	EN 1607
Specific thermal capacity	c	J/(kg·K)	1400	EN 12524
Water vapour diffusion equivalent air layer thickness	s_d	m	> 1500 (see examination report A3-04/03, FIW München)	EN 12524
Water absorption of polyurethane rigid foam after 28 days of sub-water storage	-	Vol-%	1.0 to 2.5	EN 12087
Resistance of polyurethane rigid foam	-	-	Chemically resistant to petrol, diesel mineral oil, micro-organisms, mould, rot-proof	-
Thickness grades	-	mm	20, 30, 40, 50, 60, 70, 80, 100, 120, 140, 160, 180, 200, 220, 240	-
Edge connection	-	-	Thickness 20-40 mm round about edgeless cut, Thickness 50-100 mm round about edgeless cut or with rebated joint, Thickness 120-240 mm round about with rebated joint	-
Overlap	-	mm	1200 x 600 (calculation measurement) (coverage with rebated joint is 2 cm smaller)	-

Our brochures and information material are meant to provide advice to the best of our knowledge. Subject to technical modifications.



Declaration of Performance
002-LICPR-200801
www.linzmeier.de/downloads



DIN EN 13165
Inspection: 0751 FIW München



pure life is a seal of approval issued by the UGPU association