

## Technical data

# LINITHERM PAL SIL T

Over-rafter Insulation system



Property	Formula symbol	Unit	Parameter and measured value	Standard
Material	-	-	Polyurethane rigid foam, coated with aluminium film on both sides	EN 13165
Application type	-	-	DAD	DIN 4108-10
Gross density	$\rho$	kg/m <sup>3</sup>	≥ approx. 33	-
Fire behaviour	-	-	Class E or normally inflammable	EN 13501-1
Thermal conductivity (D)	$\lambda_B$	W/(mK)	0.023	DIN 4108-4
Thermal conductivity (EU)	$\lambda_D$	W/(mK)	0.022	EN 13165
Compressive stress	$\sigma_{D10}$	N/mm <sup>2</sup> kPa	≥ 0.12 (at 10 % compression) ≥ 120	EN 826
Specific thermal capacity	c	J/(kg·K)	1400	EN 12524
Water vapour diffusion equivalent air layer thickness	$s_d$	m	> 1500 (see examination report A3-04/03, FIW München)	EN 12524
Water absorption of polyurethane rigid foam after 28 days of sub-water storage	-	Vol-%	1.0 to 2.5	EN 12087
Resistance of polyurethane rigid foam	-	-	Chemically resistant to petrol, diesel mineral oil, micro-organisms, mould, rot-proof	-
Thickness without 6 mm silicate panel	-	mm	60	-
Edge connection	-	-	Tongue & groove pressfit joints on all sides	-
Overlap	-	mm	2480 x 1180 (= calculation measurement)	-

Our brochures and information material are meant to provide advice to the best of our knowledge. Subject to technical modifications.



Declaration of Performance  
001-LICPR-200801  
[www.linzmeier.de/downloads](http://www.linzmeier.de/downloads)



DIN EN 13165  
Inspection: 0751 FIW München



## Technical data

### Silicate panel

from LINITHERM PAL SIL T



Property	Formula symbol	Unit	Parameter and measured value	Standard
Material	-	-	Conglomerate of silicate, mineral additives and cellulose	EN 12467
Thermal conductivity	$\lambda_B$	W/(mK)	0.32	ISO 22007-2.2:2008
Fire behaviour	-	-	Class A1	EN 13501-1
Bending tensile strength	$\beta_{BZ}$	N/mm <sup>2</sup>	> 10	-
Gross density	$\rho$	kg/m <sup>3</sup>	Approx. 975 (dry density)	-
Alkalinity	-	ph-value	7–11	-
Moisture content	-	%	8	-
Change of form (air-dry - saturated)	-	%	+0.12	-
Moisture dispersant	-	%	Approx. 60	-
Edge connection	-	-	Drywall edge	-
Panel thickness	-	mm	6	-
Format	-	mm	2480 x 1180	-

Our brochures and information material are meant to provide advice to the best of our knowledge. Subject to technical modifications.

#### Advantages of the silicate panel

- Resistant to mould (growth „0“ acc. to DIN EN ISO 846)
- Moisture resistant
- Dimensionally stable
- Resistant to pest infestation
- Water vapour permeable
- Rot-proof

Note: The details stated above apply under normal conditions of use of the products. They are based on our experience to date and do not represent an assurance of properties. Existing laws/directives/provisions are to be followed by the user at his own responsibility.

## Technical data

# Sarking membrane

from LINITHERM PAL SIL T



Property	Formula symbol	Unit	Parameter and measured value	Standard
Material	-	-	3-layer PP fleece-foil combination	-
Colour top side	-	-	Grey with printed grid pattern	-
Protrusion to insulation panel	-	-	Transverse and lengthwise approx. 8 cm plus integrated factory-made sealing band	-
Classification acc. to ZVDH (Central Organisation of the German Roofing Trade)	-	-	UDB-A from a roof pitch of 20°	-
Watertightness test Technical University of Berlin	-	-	Passed	-
Water vapour diffusion equivalent air layer thickness	$s_d$	m	Approx. 0.02	EN ISO 12572
Maximum tensile strength	-	N/5 cm	Longitudinal: 360 Transverse: 270	EN 12311-1
Maximum tensile strength and deformation	-	%	Longitudinal: 70 Transverse: 50	EN 12311-1
Tear resistance (nail shaft)	-	N	Longitudinal: 220 Transverse: 290	EN 12310-1
Operating temperature range	-	°C	-40 to +100	-
Temporary roof covering	-	Week	4	-
Fire behaviour	-	-	Class E or normally inflammable	EN 13501-1
Web width	-	m	1.26	-
Weight	-	g/m <sup>2</sup>	Approx. 165	-
Resistance against water penetration	-	-	W1	EN 1928

Our brochures and information material are meant to provide advice to the best of our knowledge. Subject to technical modifications.

Note: The details stated above apply under normal conditions of use of the products. They are based on our experience to date and do not represent an assurance of properties. Existing laws/directives/provisions are to be followed by the user at his own responsibility.