



Technical data

LINITHERM PAL W

External wall insulation

Property	Formula symbol	Unit	Parameter and measured value	Standard
Material	–	–	Polyurethane rigid foam, coated with aluminium film on both sides, low-glare on one side	EN 13165
Application type	–	–	WAB, WZ	DIN 4108-10
Gross density	ρ	kg/m ³	≥ approx. 33	–
Fire behaviour	–	–	Class C-s2,d0 (corresponds to national building inspection class »flame retardant«)	EN 13501-1
Thermal conductivity (D)	λ_B	W/(mK)	0.023	DIN 4108-4
Thermal conductivity (EU)	λ_D	W/(mK)	0.022	EN 13165
Temperature resistance	–	°C	– 30 to + 90	–
Compressive stress	σ_{D10}	N/mm ² kPa	≥ 0.12 (at 10 % compression) ≥ 120	EN 826
Specific thermal capacity	c	J/(kg·K)	1400	EN 12524
Water vapour diffusion equivalent air layer thickness	s_d	m	> 1500	EN 12524
Water absorption of polyurethane rigid foam after 28 days of sub-water storage	–	Vol -%	1.0 to 2.5	EN 12087
Resistance of polyurethane rigid foam	–	–	Chemically resistant to petrol, diesel mineral oil, micro-organisms, mould, rot-proof	–
Thickness grades	–	mm	80, 100, 120, 140, 160	–
Edge connection	–	–	Round about edgeless cut or with rebated joint	–
Overlap	–	mm	1200 × 600 (coverage is 2 cm less with rebated joint)	–

Our brochures and information material are meant to provide advice to the best of our knowledge. Subject to technical modifications.

Advice on fire behavior:

Requirements from the respective state building code and from special approvals, e.g. facade cladding, must be observed!



Declaration of Performance
007-LICPR-200801
www.linzmeier.de/downloads



DIN EN 13165
Inspection: 0751 FIW München



Meets the GfG requirements for prevention of hazardous substances in insulation: "pure life" is a seal of approval issued by the GfG association.

Linzmeier Bauelemente GmbH

Industriestraße 21 D-88499 Riedlingen
Schortentalstraße 24 D-07613 Königshofen/Thüringen
Info@Linzmeier.de www.Linzmeier.de

Tel.: +49 (0) 73 71 18 06-0
Tel.: +49 (0) 3 66 91 7 22-0

TD / EN / LINITHERM PAL W
Status 2024-04