

Technical data

LINITHERM PGV

Universal insulation board



Property	Formula symbol	Unit	Parameter and measured value	Standard
Material	–	–	Polyurethane rigid foam, coated with mineral fleece on both sides	EN 13165
Application type	–	–	DAA dh or DEO dh, WZ	DIN 4108-10
Gross density	ρ	kg/m ³	≥ approx. 33	–
Fire behaviour	–	–	Class E or normally inflammable	EN 13501-1
Thermal conductivity (D)	λ_B	W/(mK)	0.029 for panel thickness < 80 mm 0.027 for panel thickness ≥ 80 to 119 mm 0.026 for panel thickness ≥ 120 mm	DIN 4108-4
Thermal conductivity (EU)	λ_D	W/(mK)	0.028 for panel thickness < 80 mm 0.026 for panel thickness ≥ 80 to 119 mm 0.025 for panel thickness ≥ 120 mm	EN 13165
Temperature resistance	–	°C	–30 to +90	–
Compressive stress	σ_{D10}	N/mm ² kPa	≥ 0.12 (at 10 % compression) ≥ 120	EN 826
Max. permitted permanent compressive stress	σ_{D2}	N/mm ² kPa	≥ 0.02 (at 2 % compression) ≥ 20	–
Tensile strength perpendicular to the panel surface	σ_{mt}	N/mm ² kPa	≥ 0.05 ≥ 50	EN 1607
Specific thermal capacity	c	J/(kg·K)	1400	EN 12524
Water vapour diffusion resistance factor	μ	–	40 / 200	DIN V 4108-4
Water absorption of polyurethane rigid foam after 28 days of sub-water storage	–	Vol-%	1.0 to 2.5	EN 12087
Resistance of polyurethane rigid foam	–	–	Chemically resistant to petrol, diesel mineral oil, micro-organisms, mould, rot-proof	–
Thickness grades	–	mm	20, 30, 40, 50, 60, 80, 100, 120, 140, 160, 180, 200	–
Edge connection	–	–	Thickness 20–40 mm round about edgeless cut, Thickness 50–100 mm round about edgeless cut or with rebated joint, Thickness 120–200 mm round about with rebated joint	–
Calculation measurement	–	mm	1200 × 600 (calculation measurement) (coverage with rebated joint is 2 cm smaller)	–

Our brochures and information material are meant to provide advice to the best of our knowledge. Subject to technical modifications.



Declaration of Performance
004-LICPR-200801
www.linzmeier.de/downloads



DIN EN 13165
Inspection: 0751 FIW München

